

## 891 Vintage Oil 經典油蠟

**Suitable surfaces:** Wood and wood materials, interior. Substrate has to be clean, dry, free from fat, oil, separative, colouring substances, chemically neutral. Sand finely, remove old coatings.

適合的塗布表面：室內的木材和木製產品。底材要保持清潔與乾燥，不含脂肪，油類，具可分離性或會染色的物質，化學中性。稍微砂磨，去除舊的塗層。

**Basic treatment:** Vintage oil no. 891, can be thinned with up to 20 % of Orange oil no. 191. **基本程序：**經典油蠟 no. 891，可至多用 20% no. 191 橘子油稀釋。

**Final treatment:** Vintage oil no. 891, undiluted.

最後程序：經典油蠟 no. 891，無須稀釋

**Application:** Apply evenly (with brush or cloth), remove excess oil within 10 minutes. Observe overcoating times between operations. If necessary, sand finely before the final treatment.

施作方式：均勻塗布(用刷子或衣物)，10 分鐘後擦去多餘油脂。在過程中觀察第二次塗佈的時間。如果需要，在最後程序前做細砂磨

**Overcoatable** after approx. 24 h. Provide for adequate ventilation during application and drying process.

等待大約 24 小時之後塗刷第二次，並在施作及乾燥過程中保持通風。

**Cleaning of tools:** With Diluent no. 191. If necessary, wash again with water and Plant soap no. 411.

用具清潔方式：用 no. 191 作為稀釋劑，如果需要，用清水及 no. 411 植物皂再次清洗。

**Storage stability:** 24 months.

保存期限：24 個月

**Composition:** Orange oil (4,33%), balsamic turpentine (36,40%), linseed oil, colophony glycerol ester with organic acids, mineral fillers, mineral pigments, silica, sunflower oil, castor oil, drying agents (cobalt-free), swelling clays, lecithin, drying agents (a.o. cobalt salt), hydrogenated castor oil, alcohol.

May cause allergic reactions. Natural products are neither odourless nor emission-free.

成份：橘子油(4, 33%)，植物香脂松節油(36, 40%) 亞麻籽油，有機酸松脂甘油酯，礦物填料，礦物顏料，矽石，葵花籽油，蓖麻油，乾燥劑（無鈷），膨脹性黏土，卵磷脂，氫化蓖麻油，酒精.，

有可能造成過敏反應。天然產品非無臭無味，也非零二氧化碳排放